



**Professional  
Testing  
Laboratory  
Inc.**

<b>TEST NUMBER</b>	0030661
<b>DATE</b>	12/05/94

<b>CLIENT</b>	SUPERIOR MANUFACTURING GROUP
---------------	------------------------------

<b>TEST METHOD CONDUCTED</b>	AATCC 123 Carpet Soiling: Accelerated Soiling Method
------------------------------	------------------------------------------------------

DESCRIPTION OF TEST SAMPLE	
<b>IDENTIFICATION</b>	118 Arrow Trax
<b>COLOR</b>	-----
<b>ROLL</b>	-----
<b>CONSTRUCTION</b>	Needled Synthetic
<b>FIBER</b>	-----
<b>BACKING</b>	PVC Hardback

GENERAL PRINCIPLE:

This test method is designed to provide an accelerated means to simulate soiling similar to floor service soiling. Test specimens are tumbled with prepared soil in a sealed container for a predetermined time. After soiling, the test sample is vacuumed and a portion is cleaned by a hot water extraction method. After achieving a heavy soiling level the test sample was cleaned using detergent and a hot water extraction device. By comparing the shampooed sample to an original "control" sample, any change which may have occurred is assessed and rated by means of the AATCC Gray Scale.

TEST RESULTS:

	RATING
<b>AFTER VACUUM</b>	3
<b>AFTER CLEANING</b>	5

RATING KEY:

- 5 - Negligible or no change
- 4 - Slight change
- 3 - Noticeable change
- 2 - Considerable change
- 1 - Heavy change

RECEIVED DEC 12 1994

APPROVED BY: \_\_\_\_\_

*Gary Phillips*  
President

NVLAQ