



TEST REPORT

DATE: 09/09/2009

TEST NUMBER: 123278

CLIENT	Superior Manufacturing Group - Moselle Division
--------	---


TEST METHOD CONDUCTED	ASTM D412 Breaking Load and Elongation
-----------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	410C
COLOR	-----
ROLL	-----
CONSTRUCTION	Mat
FIBER	-----
BACKING	-----
REFERENCE	

TEST CONDITION	70°F and 65% Relative Humidity
TEST SPEED	12 inches/minute
AVERAGE SPECIMEN THICKNESS	0.390 Inch

TEST RESULTS

	BREAKING LOAD	ELONGATION
Specimen 1	28.6 Lbs	160.6%
Specimen 2	28.8 Lbs	159.2%
Specimen 3	29.1 Lbs	161.9%
Specimen 4	30.2 Lbs	164.6%
Specimen 5	28.9 Lbs	156.7%
AVERAGES	29.1 Lbs	160.6%
TENACITY		74.6 Lbs/Square Inch

APPROVED BY: 

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.