



Professional  
Testing  
Laboratory  
Inc.

TEST NUMBER: 0017457  
DATE: 10/02/92

CLIENT: SUPERIOR MANUFACTURING GROUP

TEST METHOD CONDUCTED: ASTM C 1028-89 Static Coefficient of Friction  
by the Horizontal Dynamometer Pull-Meter Method

DESCRIPTION OF TEST SAMPLE:

IDENTIFICATION: 411  
COLOR: ----  
ROLL: ----  
CONSTRUCTION: ----  
FIBER: ----  
BACKING: ----

GENERAL PRINCIPLE:

This test determines the static coefficient of friction of tile or other surfaces using a neolite heel assembly.

A neolite heel assembly with a fifty pound load is pulled horizontally with a dynamometer to measure the force required to cause the assembly to slip. After the sample is tested, measurements are calculated and reported as the static coefficient of friction.

RESULTS:

SAMPLE CONDITION: Tested As Received

HEEL ASSEMBLY CONDITION	STATIC COEFFICIENT OF FRICTION
Dry	.79

APPROVED BY: Greg Phillips, PRESIDENT

NVLAQ