



TEST REPORT

DATE: 12/03/2008

TEST NUMBER: 117908

| | |
|--------|---|
| CLIENT | Superior Manufacturing Group - Moselle Division |
|--------|---|

| | |
|-----------------------|-----------------------------------|
| TEST METHOD CONDUCTED | Compression Deflection Comparison |
|-----------------------|-----------------------------------|

| DESCRIPTION OF TEST SAMPLE | |
|----------------------------|----------------------------------|
| IDENTIFICATION | #413 Regular Dynashield Compound |
| COLOR | Black |
| ROLL | ----- |
| CONSTRUCTION | PVC Plastisol |
| FIBER | Foam Product |
| BACKING | ----- |
| REFERENCE | |

GENERAL PRINCIPLE


This test was designed to assess and compare performance characteristics of a variety of industrial mattings submitted for testing. Two specific compression load levels were applied to the test samples and the deflection which resulted was measured.

It appears that, within a reasonable range, the greater the deflection the better the anti-fatigue properties of the material. The compression load was increased to determine whether the deflection increased respectively.

TEST RESULTS

| MEASUREMENT | AVERAGE ORIGINAL THICKNESS | AVERAGE THICKNESS | DEFLECTION |
|--------------------|----------------------------|-------------------|------------|
| 20 lbs/square inch | 0.488 Inch | 0.240 Inch | 0.248 Inch |
| 40 lbs/square inch | 0.488 Inch | 0.183 Inch | 0.305 Inch |

APPROVED BY:



This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.