



TEST REPORT

DATE: 12/03/2008

TEST NUMBER: 117740

CLIENT	Superior Manufacturing Group - Moselle Division
--------	-------------------------------------------------


TEST METHOD CONDUCTED	ASTM D412 Breaking Load and Elongation
-----------------------	----------------------------------------

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	#419 Regular Dynashield Compound
COLOR	Black
ROLL	----
CONSTRUCTION	PVC Plastisol
FIBER	Foam Product
BACKING	-----
REFERENCE	V1638-82 MSE Compound

TEST CONDITION	70°F and 65% Relative Humidity
TEST SPEED	20 inches/minute
AVERAGE SPECIMEN THICKNESS	0.470 Inch

TEST RESULTS

	BREAKING LOAD	ELONGATION
Specimen 1	16.2 Lbs	137.9%
Specimen 2	17.1 Lbs	153.4%
Specimen 3	16.3 Lbs	143.6%
Specimen 4	17.9 Lbs	149.8%
Specimen 5	16.4 Lbs	151.2%
AVERAGES	16.8 Lbs	147.2%
TENACITY		71.5 Lbs./Square Inch

APPROVED BY: 

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.