



TEST REPORT

DATE: 08/09/2006

TEST NUMBER: 102373

CLIENT	Superior Manufacturing Group
--------	------------------------------


TEST METHOD CONDUCTED	ASTM D412 Breaking Load and Elongation
-----------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	550 Cushion-Ease
COLOR	Black
ROLL	-----
CONSTRUCTION	Rubber
FIBER	-----
BACKING	-----
REFERENCE	

TEST CONDITION	70°F and 65% Relative Humidity
TEST SPEED	12 inches/minute
AVERAGE SPECIMEN THICKNESS	0.762 Inch

TEST RESULTS

	BREAKING LOAD	ELONGATION
Specimen 1	33.2 Lbs	65.2 %
Specimen 2	30.7 Lbs	56.1 %
Specimen 3	33.2 Lbs	55.6 %
Specimen 4	32.6 Lbs	61.2 %
Specimen 5	36.5 Lbs	58.7 %
AVERAGES	33.2 Lbs	59.7 %
TENACITY		87.1 Lbs/Square Inch

APPROVED BY: 

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.