



TEST REPORT

DATE: 12/09/2008

TEST NUMBER: 118140

CLIENT	Superior Manufacturing Group
--------	------------------------------

TEST METHOD CONDUCTED	ASTM C1028-96 Test Method for Determining the Static Coefficient of Friction by the Horizontal Dynamometer Pull-Meter Method
-----------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Sanitop 1/2"
COLOR	Black
ROLL	562S0035BL
CONSTRUCTION	Rubber
FIBER	-----
BACKING	-----
REFERENCE	

GENERAL PRINCIPLE

This test determines the static coefficient of friction of tile or other surfaces using a neolite heel assembly.

A neolite heel assembly with a 50 pound load is pulled horizontally with a dynamometer to measure the force required to cause the assembly to slip. After the sample is tested, measurements are calculated and reported as the static coefficient of friction.

TEST RESULTS

SAMPLE CONDITION	Tested As Received
------------------	--------------------

HEEL ASSEMBLY CONDITION	STATIC COEFFICIENT OF FRICTION
Dry	0.59
Wet	0.49

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.