



Professional
Testing
Laboratory
Inc.

TEST NUMBER: 0015527
DATE: 06/26/92

CLIENT: SUPERIOR MANUFACTURING GROUP

TEST METHOD CONDUCTED: ASTM C 1028-89 Static Coefficient of Friction
by the Horizontal Dynamometer Pull-Meter Method

DESCRIPTION OF TEST SAMPLE:

IDENTIFICATION: 750
COLOR: -----
ROLL: -----
CONSTRUCTION: -----
FIBER: -----
BACKING: -----

GENERAL PRINCIPLE:

This test determines the static coefficient of friction of tile or other surfaces using a neolite heel assembly.

A neolite heel assembly with a fifty pound load is pulled horizontally with a dynamometer to measure the force required to cause the assembly to slip. After the sample is tested, measurements are calculated and reported as the static coefficient of friction.

RESULTS:

SAMPLE CONDITION: Tested As Received

HEEL ASSEMBLY CONDITION	STATIC COEFFICIENT OF FRICTION
Dry	.73

APPROVED BY: Gary Colony, PRESIDENT

NVLAQ

RECEIVED JUN 29 1992