



### TEST REPORT

DATE: 09/27/2010

TEST NUMBER: 132475

CLIENT	Superior Manufacturing Group - Moselle Division
--------	---

TEST METHOD CONDUCTED	ASTM D2240-05 Test Method for Rubber Property - Durometer Hardness
-----------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	#782-Sept-2010
COLOR	-----
ROLL	-----
CONSTRUCTION	-----
FIBER	-----
BACKING	Attached Cushion
REFERENCE	

#### GENERAL PRINCIPLE

The hardness of a test sample is measured by means of a Type A Shore Durometer. The Durometer measures the penetration of its specified indenter forced into the test material under specified conditions.

A relationship between tested materials exists only when the same type of Durometer is used.

#### TEST RESULTS

INDENTATION HARDNESS	95
----------------------	----

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.