



### TEST REPORT

DATE: 12/14/2009

TEST NUMBER: 125270

CLIENT	Superior Manufacturing Group - Moselle Division
--------	---

TEST METHOD CONDUCTED	ASTM D570-98 Standard Test Method for Water Absorption of Plastics
-----------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	#830-Bilt-2009
COLOR	-----
ROLL	-----
CONSTRUCTION	-----
FIBER	-----
BACKING	-----
REFERENCE	

#### GENERAL PRINCIPLE

This test method covers the determination of the absorption of water by a test specimen when immersed in water. The specimen is immersed in 23° C distilled water for 24 hours. The difference in weight is determined and calculated as a percentage gained or lost from the water immersion.

#### TEST RESULTS

ORIGINAL WEIGHT	76.22 grams
FINAL WEIGHT	76.38 grams
WEIGHT LOSS OR GAIN	0.16 grams (0.21% gain)

APPROVED BY:



This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.