



TEST REPORT

DATE: 09/10/2004

TEST NUMBER: 091282

CLIENT	Superior Manufacturing Group
TEST METHOD CONDUCTED	ASTM D2240-02 Test Method for Rubber Property – Durometer Hardness

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	556 Cushion Ease Solid 3x3
COLOR	Black
ROLL	----
CONSTRUCTION	Rubber
FIBER	----
BACKING	----
REFERENCE	

GENERAL PRINCIPLE

The hardness of a test sample is measured by means of a Type A Shore Durometer. The Durometer measures the penetration of its specified indenter forced into the test material under specified conditions.

A relationship between tested materials exists only when the same type of Durometer is used.

TEST RESULTS

INDENTATION HARDNESS	67
-----------------------------	----

APPROVED BY: *Gary Osburn*

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.