



Professional  
Testing  
Laboratory  
Inc.

## TEST REPORT

DATE: 09/10/2004

TEST NUMBER: 091282

CLIENT	Superior Manufacturing Group
--------	------------------------------

TEST METHOD CONDUCTED	ASTM D1004-94a-03 Test Method for Initial Tear Resistance of Plastic Film and Sheeting
-----------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	556 Cushion Ease Solid 3x3
COLOR	Black
ROLL	----
CONSTRUCTION	Rubber
FIBER	----
BACKING	----
REFERENCE	

### GENERAL PRINCIPLE

This test method covers the determination of the tear resistance of flexible plastic film and sheeting at very low rates of loading. The test is designed to measure the force to initiate tearing. The maximum stress, usually found near the outset of tearing, is recorded as the tear resistance in pounds (force).

### TEST RESULTS

SAMPLE THICKNESS	.787 inch
TEST SPEED	20 inches/minute
AVERAGE TEARING STRENGTH	55.4 lbs.

APPROVED BY: \_\_\_\_\_

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.