

# TEST REPORT

COPY

25/12/2024

Fire Test No. S1131590

To

Manufacturer Name: JUSTRITE SAFETY GROUP

Manufacturer Address: Achterzeedijk 57-1, 2992SB Barendrecht, The Netherlands

金
會
 Foundation of Fire Retardant Safety Center  
 1F., No. 42, Ln. 76, Sec. 3, Zhongyang Rd., Tucheng Dist., New  
 President of FFRSC: HUNG CHUN-AN

Received on: 17/12/2024

*Hung Chun-An*

<span style="font-size: 2em;">基</span> Basic Information of Sample <span style="float: right; font-size: 2em;">專</span>						
Kinds of Products	CARPET	Product Name	537			
Material, Percentage	PVC 100%	Shape of Pile (Height of Pile)	12mm <span style="font-size: 2em;">法</span>			
<span style="font-size: 2em;">心</span> Test Results Table						
Test Items Specimen Direction and No.	Afterflame Time /sec (X ≤ 20)	Charred Length /cm (X ≤ 10)	Test Items Specimen Direction and No.	Afterflame Time /sec (X ≤ 20)	Charred Length /cm (X ≤ 10)	人
<span style="font-size: 2em;">中</span> Warp	1	0	Weft	1	4	2
	2	0		2	3	3
	3	0		3	3	<span style="font-size: 2em;">防</span>
<span style="font-size: 2em;">全</span> Note	1. Method: Flameproof Testing Standards of Flameproof Products or Its Materials-2023 (Ministry of the Interior, R.O.C) 2. Burning time: 30sec 3. The sample information is provided by the applicant. 4. The test report shall not be reproduced in abstract form without the consent of the Laboratory, except for full-text reproduction. 5. This report is not intended for use in litigation. 6. The test data and results in this report do not take into account measurement uncertainties and risk levels.					
Determination	PASSED					
Date of Testing Activities	20/12~18/12/2024		Test Number	SB-13-1276		
Approval Signature	<span style="font-size: 2em;">依</span> <span style="font-size: 2em;">婷</span> <span style="font-size: 2em;">許</span>					

