

# **ASTM D1335-98**

## **TEST METHOD FOR TUFT BIND OF PILE YARN FLOOR COVERING**

### **GENERAL PRINCIPLE**

This test method is designed to measure the force required to pull a tuft completely out of a pile floor covering. It is applicable to both cut and looped pile construction.

### **TEST RESULTS**

<b>AVERAGE TUFT BIND</b>	10 Lbs
--------------------------	--------

### **INTERPRETATION OF THE RESULTS**

1 Lbs = 0.64 kg

So, in this case the force required to pull the tuft completely out of the pile floor covering is 10 Lbs.

The most meaningful interpretation is to compare the Graves Tear Strength results of all NOTRAX® Industrial Floor Matting products.

All testing of NOTRAX® Floor Matting has been performed by an independent testing laboratory.